



GOLDEN EAGLE CHEMICAL, INC.  
400 Paredes Line Rd. Suite 5, Brownsville, Texas, 78521 U.S.A.

## PRODUCT DATA SHEET

### APO-SJ-120

PROPERTY	ASTM TEST METHOD	TYPICAL PROPERTIES
Viscosity, SUS @ 100F°	D2161	12400
Viscosity, SUS @ 210 F°	D2161	120
Viscosity, cSt @ 40C°	D445	2036
Viscosity, cSt @ 100C°	D445	23.77
API Gravity	D287	9.5
Specific Gravity @ 60F°	D1250	1.0035
Density, lb/ Gallon @ 60 F°	D1250	8.358
Color	D1500	D 8.0
Flash, C.O.C. F°	D92	420
Pour Point, F°	D97	60
Aniline Point, F°	D611	88
Refractive Index@ 20 C°	D1218	1.5660
Refractivity Intercept	D2140	1.067
Viscosity-Gravity Constant	D2501	0.952
Neut. No.,mg KOH/g	D974	7.0
Clay-Gel Analysis, w %	D2007	
Asphaltenes		0
Polar Compounds		21
Aromatic		65
Saturates		14
Carbon-Type Analysis, %	D2140	
Ca		42
Cn		36
Cp		22

# GEOTECH