



GOLDEN EAGLE CHEMICAL, INC.
400 Paredes Line Rd. Suite 5, Brownsville, Texas, 78521 U.S.A.

PRODUCT DATA SHEET

APO-SJ-90

PROPERTY	ASTM TEST METHOD	TYPICAL PROPERTIES
Viscosity, SUS @ 100F°	D2161	3852
Viscosity, SUS @ 210 F°	D2161	81.9
Viscosity, cSt @ 40C°	D445	662
Viscosity, cSt @ 100C°	D445	15.34
API Gravity	D287	10.9
Specific Gravity @ 60F°	D1250	0.9937
Density, lb/ Gallon @ 60 F°	D1250	8.276
Color	D1500	D 8.0
Flash, C.O.C. F°	D92	410
Pour Point, F°	D97	45
Aniline Point, F°	D611	99
Refractive Index@ 20 C°	D1218	1.5535
Refractivity Intercept	D2140	1.0650
Viscosity-Gravity Constant	D2501	0.946
Neut. No.,mg KOH/g	D974	5.5
Clay-Gel Analysis, w %	D2007	
Asphaltenes		0
Polar Compounds		17
Aromatic		65
Saturates		18
Carbon-Type Analysis, %	D2140	
Ca		41
Cn		38
Cp		21

GEOTECH