



GOLDEN EAGLE CHEMICAL, INC.
400 Paredes Line Rd. Suite 5, Brownsville, Texas, 78521 U.S.A.

PRODUCT DATA SHEET

Pale Oil 4000

PROPERTY	ASTM TEST METHOD	TYPICAL PROPERTIES
Color	D1500	2.0
Appearance	Visual	Pass
Viscosity @ 40°C, cSt	D445	4128
Viscosity @ 100°C, cSt	D445	40.86
Viscosity @ 100 °F, SUS	D2161	25,136
Viscosity @ 210 °F, SUS	D2161	201
Flash, PM ° C	D93	235
Flash, PM ° F	D93	460
Aniline Point, ° F	D611	181
Paraffinic Carbon Atoms % Wt.	D2140	35.2
Naphthenic Carbon Atoms % Wt.	D2140	49.2
Aromatic Carbon Atoms % Wt.	D2140	15.6
Specific Gravity, 60 °F	D4052	.9679
Gravity, API @ 60°F	D1250	14.8
Lbs. Per Gallon @ 60°F	Calculated	8.055