



GOLDEN EAGLE CHEMICAL, INC.  
400 Paredes Line Rd. Suite 5, Brownsville, Texas, 78521 U.S.A.

## PRODUCT DATA SHEET

### Solvent Neutral 250

| PROPERTY                | ASTM TEST METHOD | TYPICAL PROPERTIES |
|-------------------------|------------------|--------------------|
| Color                   | D1500            | L1.5               |
| Viscosity @ 100°F, SUS  | D2161            | 263                |
| Viscosity @ 210°F, SUS  | D2161            | 50.1               |
| Viscosity @ 40°C, cSt   | D445             | 50.9               |
| Viscosity @ 100°C, cSt  | D445             | 7.131              |
| Viscosity Index         | D2270            | 97                 |
| Flash, COC°C            | D92              | 232                |
| Pour Point, °C          | D97              | -12                |
| Aromatic Carbon %       | D2140            | 16                 |
| Naphthenic Carbon %     | D2140            | 34                 |
| Paraffinic Carbon %     | D2140            | 50                 |
| Specific Gravity @ 60°F | D4052            | 0.8690             |
| Gravity, API @ 60°F     | D287             | 31.2               |
| Lbs. Per Gallon         | Calculated       | 7.243              |